

17
AD-A263 326

DOCUMENTATION PAGE

Form Appro
OMB No. 07

12

This is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and reviewing the collection of information, sending comments regarding this burden estimate or any other aspect of this collection of information, including this burden estimate, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

2. REPORT DATE

September 15, 1992

3. REPORT TYPE AND DATES COVERED

End of Contract, Sept. 88-Sept. 91

4. TITLE AND SUBTITLE

Applications of Scanning Tunneling Microscopy to Electrochemistry

5. FUNDING NUMBERS

N00014-88-K-0482,
Mod/Amend: P00001

6. AUTHOR(S)

M. J. Heben, T. L. Longin, R. Pyllki, R. M. Penner,
R. Blumenthal, and N. S. Lewis

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

California Institute of Technology
Division of Chemistry and Chemical Engineering
Mail Code: 127-72
Pasadena, California 911258. PERFORMING ORGANIZATION
REPORT NUMBER

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Dr. Ronald A. De Marco
Chemistry Division
Office of Naval Research
800 North Quincy Street
Arlington, Virginia 22217-500010. SPONSORING / MONITORING
AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION / AVAILABILITY STATEMENT

This document has been approved for public release and sale; its distribution is unlimited

12b. DISTRIBUTION CODE

13. ABSTRACT (Maximum 200 words)

1

14. SUBJECT TERMS

15. NUMBER OF PAGES

16. PRICE CODE

17. SECURITY CLASSIFICATION
OF REPORT18. SECURITY CLASSIFICATION
OF THIS PAGE19. SECURITY CLASSIFICATION
OF ABSTRACT

20. LIMITATION OF ABSTRACT

OFFICE OF NAVAL RESEARCH
END-OF-CONTRACT REPORT
PUBLICATIONS/PATENTS/PRESENTATIONS/HONORS/STUDENT REPORT

for

Contract N00014-88-K-0482, Mod/Amend: P00001

R&T Code ~~413d017~~ 413h008---04

Applications of Scanning Tunneling Microscopy to Electrochemistry

Nathan S. Lewis
California Institute of Technology
Department of Chemistry
Pasadena, California 91125

September 15, 1992

DD FORM 101-2 (10-80) PREVIOUS EDITIONS OBSOLETE

Accession For	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

Reproduction in whole, or in part, is permitted for any purpose of the United States Government.

*This document has been approved for public release and sale; its distribution is unlimited.

93 4 26 09 9

93-08955



End of Contract Report for ONR Contract N00014-88-K-0482

Our efforts through the last contract period have involved the fundamental study of the STM imaging process, the investigation of the use of partially insulated STM tips as ultramicroelectrodes,^{1,2} and applications of STM for the generation of lithographic features.³ STM investigations of conducting polymers dispersed on graphite surfaces and doped with I₂ revealed that, although the conducting backbone of the polymer could be imaged under a range of tunnelling conditions, the non-conducting side groups of the polymer were not imaged. These images represent the first atomic resolution images of polymers, and studies of this type, involving the simultaneous imaging of nominally conducting and non-conducting groups, should prove essential in developing a theoretical understanding of the contrast mechanisms which dominate the imaging of individual adsorbed molecules with STM. Studies of ultramicroelectrodes, fabricated initially as partially insulated STM tips for use in solutions containing significant concentrations of electroactive species, have revealed the possibility of fabricating electrodes as small as one nanometer in diameter. Such tips, assuming a reproducible and well defined exposed metal area, may be used to make fundamental measurements of electrochemical processes,⁴ such as the electron transfer rate constant for Ru(NH₃)₆^{3+/2+} redox couple. The results of these investigations are currently being carefully reproduced in our laboratories, and only after intense scrutiny will it be possible to fully assess the utility of this new method of ultramicroelectrode fabrication. The final aspect of this work has been the systematic study of process of surface nanolithography on graphite using STM methods. In these experiments, a short bias pulse, typically 20μs in duration and 4V in amplitude, is superimposed on the normal tunneling bias of ~100mV, resulting in the generation of a small ~40Å pits in the surface. In contrast to earlier studies performed in air or other gaseous environment,⁵ a reproducible amplitude threshold for feature generation is observed when the experiment is carried out in pure water.³ This threshold has been determined to be 4.0 ± 0.2 V. Further, application of a threshold pulse under water has been found to generate a new type of domed feature. This domed feature has the one unusual property, that although it remains stable for extended periods of tunneling at biases up to 500mV, application of a second bias pulse of only 200mV on one of these domed features will convert it to the familiar pit feature. We believe that both the pits and domes may be converted into sites for the chemical linkage of individual molecules on an otherwise flat and ordered region of a surface.⁶ This application would have widespread use for the imaging of large biological molecules which cannot typically be found isolated on a surface.

References

- (1) Heben, M. J.; Dovek, M. M.; Lewis, N. S.; Penner, R. M.; Quate, C. F. *J. Microsc.* **1988**, *152*, 651-661.
- (2) Penner, R. M.; Heben, M. J.; Lewis, N. S. *Anal. Chem.* **1989**, *61*, 1630.
- (3) Penner, R. M.; Heben, M. J.; Lewis, N. S.; Quate, C. F. *Appl. Phys. Lett.* **1991**, *58*, 1389-1391.
- (4) Heben, M. J.; Penner, R. M.; Lewis, N. S.; Dovek, M. M.; Quate, C. F. *Appl. Phys. Lett.* **1989**, *54*, 1421-1423.
- (5) Albrecht, T. R.; Dovek, M. M.; Kirk, M. D.; Lang, C. A.; Quate, C. F.; Smith, D. P. E. *Appl. Phys. Lett.* **1989**, *55*, 1727-1729.
- (6) Blumenthal, R.; Penner, R. M.; Heben, M. J.; Lewis, N. S. In *Scanned Probe Microscopy*; A. K. Wickramasinghe, Ed.; American Institute of Physics: New York, 1992; pp 248-252.

Personnel Funded by Contract N00014-88-K-0482

Michael J. Heben, Graduate Student
Teresa L. Longin, Graduate Student
Russell Pyllki, Graduate Student
Reginald M. Penner, Postdoctoral Fellow
Rik Blumenthal, Postdoctoral Fellow
Nathan S. Lewis, Professor of Chemistry